

**Amendments to the Claims**

Claim 1. (**Currently Amended**) A method of preparing a biodegradable polymeric delivery system for delivering a biologically active agent to a subject, wherein the biodegradable polymeric delivery system maintains a pH of greater than 3 during biodegradation of the polymeric delivery system over a period of 4 weeks, comprising:

a) forming a polymer solution comprising a solvent and a poly(lactide-*co*-glycolide) (PLGA) polymer which comprises from 50% to 100% lactide or lactic acid and from 50% to 0% glycolide or glycolic acid, wherein said lactide or lactic acid is selected from the group consisting of the L isomer, the D isomer, or a D,L racemic mixture;

b) ~~blending from 10% to 30% (w/w) of~~ a pore forming agent selected from the group consisting of PEG, poloxamer, and combinations thereof, with the PLGA polymer solution at a level from 10% to 30% (w/w, pore forming agent/polymer) to provide a resulting solution comprising the polymer and pore forming agent;

c) dispersing the biologically active agent in the resulting polymer solution; and

d) solidifying the polymer from the resulting polymer solution to provide a biodegradable polymeric system whose microclimate maintains a pH of greater than 3 during biodegradation of the polymeric system for at least 4 weeks.

Claim 2. (**Original**) The method of claim 1 wherein from 20 to 30% of the pore-forming agent is blended with PLGA polymer solution.

Claim 3. (**Original**) The method of claim 1 wherein the pore forming agent is polyethylene glycol having a molecular weight of from 500 to 30, 000.

Claim 4. (**Original**) The method of claim 1 wherein the polyethylene glycol has a molecular weight of from 4000 to 10,000.

Claim 5. (**Original**) The method of claim 1 wherein the pore forming agent is a water-soluble poloxamer having a molecular weight of from 500 to 30, 000.

Appl. No. 10/700,107  
Amdt. dated December 1, 2006  
Reply to Office Action of June 1, 2006

Claim 6. **(Original)** The method of claim 1 wherein the poloxamer has a molecular weight of from 4000 to 10,000.

Claim 7. **(Previously presented)** The method of claim 1 wherein the polymer comprises 100% lactic acid or lactide and wherein between 10% and 20% PEG is added to the polymer solution.

Claims 8-25 (Canceled)